
LANmark-OF TB OFNP 2-48C - 아시아 태평양 지역

LANMARK-OF 타이트 버퍼 실내용 6X 단일모드 9/125 G.652.D 플레넘, OFNP



Aginode Ref: N174.022NP

- 타이트 버퍼 실내용 광섬유 케이블, 실내용 케이블
- 설치가 용이한 아라미드 원사
- 직접 종단 및 접합이 가능하도록 설계됨
- 6개의 광섬유

적용 분야

LANmark-OF Tight buffer Indoor는 900 um 버퍼 코팅이 된 광섬유를 사용합니다. 이 두 번째
900 µm까지 이어지는 이 두 번째 코팅은 광섬유를 추가로 보호하며,
패치 패널에서 광섬유를 종단 처리할 때 취급이 용이합니다. 간편한 스트립 방식의 타이트 버퍼
설계로 인해 한 번의 동작으로 10 cm 이상의 광섬유를 스트리핑할 수 있습니다.
LANmark-OF Tight buffer Indoor는
무산소(anaerobic) 또는 핫멜트(hot melt) 커넥터를 사용하여 직접 종단하는 데 가장 적합합니다. 타이트 버퍼 광섬유는
피그테일 접합을 통해 종단 처리할 수도 있습니다.
LANmark-OF Tight Buffer Indoor의 건식 구조는 수직 및
수평 설치가 모두 가능합니다. 이 제품은 실내 광섬유 요구 사항을 준수합니다. 또한 이 케이블은
는 당김 방식을 통해 덕트 내에도 설치할 수 있습니다.

구조

단면도 설명:

1. 광섬유 (900 um)
2. 아라미드사
3. PVC OFNP 재질의 외부 피복

STANDARDS

ANSI/TIA-568-C.3
IEC 60793-2-10
ISO/IEC 11801

All drawings, designs, specifications, plans and particulars of weights, size and dimensions contained in the technical or commercial documentation of Aginode is indicative only and shall not be binding on Aginode or be treated as constituting a representation on the part of Aginode.

LANmark-OF 타이트 버퍼 실내용 6x 단일모드 9/125 G.652.D 플레넘 , OFNP

Characteristics

구조적 특성	
Fiber optic type	SM (G.652D)
색상	노란색
치수	
Number of optical fibres	6
외경	4.9 mm
Weight	25 g
기계적 특성	
Mechanical resistance to impacts (IEC 60794-1-E4)	100 impacts of 1 N.m
Maximum pulling force (IEC 60794-1-2-E1)	460 N
Crush resistance (IEC 60794-1-E3)	1000 N/100mm
사용 특성	
Installation temperature, range	0...40 °C
Storage temperature, range	-30...70 °C
操作温度范围	-20...60 °C
Minimum dynamic operating bending radius	98.0 mm
Minimum static operating bending radius	49 mm

All drawings, designs, specifications, plans and particulars of weights, size and dimensions contained in the technical or commercial documentation of Aginode is indicative only and shall not be binding on Aginode or be treated as constituting a representation on the part of Aginode.